

PRIMER



UNIVERSAL PRIMER FOR ACRYLIC ADHESIVE TAPES

UNOBTRUSIVE

Transparent, thanks to the solvent - free acrylic dispersion mixture.

PRACTICAL

Ready to use, compensates for irregularities on rough surfaces and guarantees fast drying.



TECHNICAL DATA

Properties	value	USC conversion
Composition	acrylic dispersion without solvents	-
Density EN 542 +20 °C	approx. 1,02 g/cm ³	0.59 oz/in ³
Viscosity	approx. 1700 mPa·s	-
Time required for complete drying (20 °C / 50 %RH)	approx. 15 min	-
Application temperature (cartridge)	+5 / +30 °C	+41 / +86 °F
Application temperature (ambient and support)	-10 / +30 °C	+14 / +86 °F
Temperature resistance once dried	-30 / +80 °C	-22 / +176 °F
French VOC classification	A+	-
Emicode (GEV test procedure)	EC1+	-
VOC content	0% - 0 g/L	-
Transport temperature	-26 / +35 °C	-14.8 / +95 °F
Storage temperature ⁽¹⁾	+15 / +25 °C	+59 / +77 °F

⁽¹⁾Store the product in a cool, dry place for no more than 12 months. Check the expiry date on the cartridge.

Waste classification (2014/955/EU): 08 04 16.

EUH208 Contains CAS 55965-84-9 (3:1), CAS 2634-33-5. May produce an allergic reaction; EUH210 Safety data sheet available on request.

CODES AND DIMENSIONS

CODE	content [mL]	yield [mL/m ²]	content [US fl oz]	yield [US fl oz/ft ²]	
PRIMER	1000	100 / 200	33.81	0.32 / 0.63	6



PACKAGING

The new packaging allows immediate installation without the need for additional tools.

RE-CLOSABLE

The cap seals the package hermetically, ensuring longer product life and preventing accidental spillage during transport.