

# SUPERB GLUE

## HIGH ELASTICITY ADHESIVE GLUE FOR SEALING MEMBRANES



### HIGH PERFORMANCE

Adhesion and elasticity stable over time, free of solvents and harmful substances. Storage and use at low temperatures possible.

### MAXIMUM ELASTICITY

Formula designed to ensure elasticity and adhesion even after drying.



## TECHNICAL DATA

Properties	value	USC conversion
Colour (wet)	light blue	-
Colour (dry)	transparent blue	-
Composition	modified acrylate-polymer dispersion	-
Density EN 542 +20 °C	approx. 1,02 g/cm <sup>3</sup>	0.59 oz/in <sup>3</sup>
Yield with strip Ø8 mm (cartridge 310 mL)	6,2 m	20.34 ft
Yield with strip Ø8 mm (cartridge 600 mL)	11,9 m	39.04 ft
Film formation time	permanently adhesive	-
Time required for drying 20 °C / 50 %RH	48 hours	-
Temperature resistance once dried	-30 / +80 °C	-22 / +176 °F
Application temperature (cartridge)	+5 / +30 °C	-13 / +86 °F
Application temperature (ambient)	-5 °C	23 °F
Application temperature (support)	+5 / +30 °C	-13 / +86 °F
Solvents	no	-
Emicode (GEV test procedure)	EC1 plus	-
French VOC classification	A+	-
Transport temperature	-30 °C / +40 °C	-22 °F / +104 °F
Storage temperature <sup>(1)</sup>	+5 °C / +25 °C	+41 °F / +77 °F
Storage time <sup>(2)</sup>	up to 24 months	-


<sup>(1)</sup>Store the product in a dry, covered location.

<sup>(2)</sup>Check the expiry date on the cartridge.


Waste classification (2014/955/EU): 08 04 10.

EUH208 Contains CAS 55965-84-9 (3:1), CAS 2634-33-5. May produce an allergic reaction; EUH210 Safety data sheet available on request.

## CODES AND DIMENSIONS

CODE	content [mL]	content [US fl oz]	version	
SUPERBGLUE310	310	10.48	rigid cartridge	20
SUPERBGLUE600	600	20.29	soft cartridge	20

## ■ GLUE PROPERTIES



### PERMANENT ADHESION | DIN 4108-11

The glue is tested for elastic and durable seals using DIN tests.

### EMICODE EC1 PLUS

Thanks to the special formulation, it achieves the highest level of safety with regard to emissions that are harmful to health.